

PUB-NO: JP409324258A  
DOCUMENT-IDENTIFIER: JP 09324258 A  
TITLE: NITRIDED PARTS

PUBN-DATE: December 16, 1997

INVENTOR-INFORMATION:

NAME	COUNTRY
<u>KUREBAYASHI, YUTAKA</u>	
MATSUMURA, KOJI	
NAKAMURA, SADAYUKI	
MIZUNO, YOSHIKI	
AMANO, MASAKI	

ASSIGNEE-INFORMATION:

NAME	COUNTRY
DAIDO STEEL CO LTD	
HONDA MOTOR CO LTD	
APPL-NO: JP08141468	
APPL-DATE: June 4, 1996	

INT-CL (IPC): C23C 8/26; C22C 38/00; C22C 38/18; C22C 38/50; C22C 38/60

ABSTRACT:

PROBLEM TO BE SOLVED: To provide nitrided parts excellent in machinability and nitriding properties of the steel even if normalizing treatment after hot forging is omitted and furthermore excellent in fatigue characteristics an bending straightening properties.

SOLUTION: A steel having a ferritic-pearlitic structure in which the average dimension of the crystal grains of ferrite is regulated to  $\leq 50\mu\text{m}$  and the average dimension of the crystal grains of pearlite is regulated to  $\leq 50\mu\text{m}$  as hot-forged and having a compsn. contg. 0.15 to 0.40% C,  $\leq 0.50\%$  Si, 0.20 to 1.50% Mn and 0.05 to 0.50% Cr, and the balance Fe with inevitable impurities is prepd. The steel is subjected to gas soft-nitriding treatment to regulate the average hardening depth to  $\leq 0.3\text{mm}$  and the fluctuation of the hardening depth to  $\leq 0.1\text{mm}$ . The steel may contain  $\leq 0.50\%$  Ni,  $\leq 0.50\%$  Mo, 0.005 to 0.030% N,  $\leq 0.3\%$  V,  $\leq 0.3\%$  Nb,  $\leq 0.2\%$  Ti,  $\leq 0.2\%$  Zr,  $\leq 0.2\%$  Ta, 0.01 to 0.3% S,  $\leq 0.3\%$  Pb,  $\leq 0.05\%$  Ca,  $\leq 0.2\%$  Bi and  $\leq 0.05\%$  Te.

COPYRIGHT: (C)1997, JPO